

ZISAMIDE®

POLYAMIDE 6

Properties	Unit	TP4204	TP4208	TP4209	TP4210
相對黏度 Relative viscosity	-	2.30±0.05	2.45±0.05	2.55±0.05	2.45±0.05
含水量 Moisture content	ppm	< 1000	< 1000	< 1000	< 1000
可萃取物 Extractable	%	< 0.6	< 0.6	< 0.6	< 0.6
胺基 Amino end group	meq/kg	44±3	44±3	42±3	42±3
密度 Density	g/cm ³	1.12 ~ 1.15	1.12 ~ 1.15	1.12 ~ 1.15	1.12 ~ 1.15
容積密度 Bulk density	kg/m ³	ca. 650	ca. 650	ca. 650	ca. 650
熔點 Melting point	°C	220	220	220	220
熔融指數 MVR	cm ³ /10min	85 ~ 105 (235°C/5.0kg)	70 ~ 90 (235°C/5.0kg)	40 ~ 80 (235°C/5.0kg)	160 ~ 200 (275°C/5.0kg)

Packaging: 800 kgs Jumbo Bag <16mt / 20' Container>

25 kgs Small Bag <15mt / 20' Container>

2024